



SG-INF-102

**MATERIAL GRADE SG H/T 60
SILICONE FDA COMPLIANT**

INFLATED HEIGHT	21mm
WORKING PRESSURE	15 PSI MAX
SEAL GROOVE MACHINED	17mm
MINIMUM RADIUS OUT	50
MINIMUM RADIUS IN	50
MINIMUM RADIUS AXIAL	90
BEND RADS DEPEND ON INFLATION DIRECTION	

PROPERTIES TEASTED POST CURED
FOR MIN 4 HOURS AT 180C

IRHD	60 SHORE
TENSILE	10N/mm2
ELONGATION AT BREAK	580%
TEAR	42N/mm
REBOUND RESILIENCE	1.2
STANDARD GRADE (MIN/MAX WORKING PRESSURE)	-40c +250c

FDA (FOOD AND DRUG ADMINISTRATION,
UNITED STATES) CODE OF FEDERAL
REGULATION, 177.260

Crystal Rubber
Unit 22, Kingsland Grange,
Woolston,
Warrington, WA1 4RW

TEL: +44 (0) 1925 825552
FAX: +44 (0) 1925 818632
EMAIL: info@crystalrubber.co.uk