

# PE500 Sheet Pressed and Planed

Green / Red / Blue / Yellow / Natural / Burgundy

## Technical Sheet



	Test Method	Unit	Value
Molecular weight	-	10 <sup>6</sup> g/mol	0.5
Density	DIN 53479 ISO 1183	g/cm <sup>3</sup>	0.95
Yield tension	DIN 53 455 ISO 527-1	N/mm <sup>2</sup>	27
Elongation at yield	DIN 53 455 ISO 527-1	%	9
Elongation at break	DIN 53 455 ISO 527-1	%	> 600
Tensile modulus of elasticity	DIN 53 455 ISO 527-1	N/mm <sup>2</sup>	1200
Ball indentation hardness	DIN 53 456 ISO 2039	N/mm <sup>2</sup>	50
Charpy impact value	DIN 53 456 ISO 179	KJ/m <sup>2</sup>	25
Attrition	Sand-Slurry procedure	-	< 400
Coefficient of friction	DIN 53 375	-	0.2
Hardness shore D	DIN 53 505	-	65
Min. permanent temperature		°C	-60
Max. permanent temperature		°C	80
Thermal length expansion coefficient (23°C - 80°C)	DIN 53 752-A	K <sup>-1</sup>	1,5 ... 2x10 <sup>-4</sup>
Thermal conductivity		E / (m x K)	0.4

# PE500 Sheet Pressed and Planed

Green / Red / Blue / Yellow / Natural / Burgundy

## Technical Sheet



Volume resistivity	DIN 53 482	Ohm x cm	$> 10^{14}$
Absorption of water	DIN 53 492	mg	$\leq 0,01$
Physiologically stable	BgVV- recommendation III	-	Ja*

All The above information is for guide purposes only. The data has been taken from standard test results provided by manufactures.