



KLINGERSil C-4408

Typical Specifications

Compressibility ASTM F 36 A		8%
Recovery ASTM F 36 A		50%
Stress relaxation DIN 52913	50MPa, 16h/300°C	28MPa
Klinger cold/hot compression 50MPa	Thickness decrease 23°C decrease at 300°C	10% 22%
Gas leakage according to DIN 3535/6		2.5ml/min
Chlorides (soluble)		150ppm
Thickness increase after fluid Immersion ASTM F 146	Oil no.3:5h/150°C Fuel B:5h/23°C	5% 5%
Density		1.9g/cm ³