



KLINGERSil C-4409

Typical Specifications

Compressibility ASTM F 36 A		7.5%
Recovery ASTM F 36 A		50%
Stress relaxation DIN 52913	50MPa, 16h/300 ⁰ C	35MPa
Klinger cold/hot compression 50MPa	Thickness decrease 23 ⁰ C decrease at 300 ⁰ C	8% 15%
Gas leakage according to DIN 3535/6		2.0ml/min
Chlorides (soluble)		150ppm
Thickness increase after fluid Immersion ASTM F 146	Oil no.3:5h/150 ⁰ C Fuel B:5h/23 ⁰ C	3% 5%
Density		2.0g/cm ³