



## KLINGERSil C-4438

### Typical Specifications

Compressibility ASTM F 36 A		8%
Recovery ASTM F 36 A		55%
Stress relaxation DIN 52913	50MPa, 16h/300°C	35MPa
Klinger cold/hot compression (50MPa)	Thickness decrease 23°C	8%
	decrease at 300°C	6%
Gas leakage according to DIN 3535/6		2.5ml/min
Chlorides (soluble)		150ppm
Thickness increase after fluid	Oil nr.3:5h/150°C	5%
Immersion ASTM F 146	Fuel B:5h/23°C	5%
Density		1.9g/cm <sup>3</sup>