



KLINGERSil C-4509

Typical Specifications

Compressibility ASTM F 36 A		12%
Recovery ASTM F 36 A		70%
Stress relaxation DIN 52913	50MPa, 16h/300°C	39MPa
Klinger cold/hot compression 50MPa	Thickness decrease 23°C decrease at 300°C	9% 7%
Chlorides (soluble)		150ppm
Thickness increase after fluid Immersion ASTM F 146	Oil nr.3:5h/150°C Fuel B:5h/23°C	3% 5%
Density		2.0g/cm ³