



KLINGERSil C-4509L

Typical Specifications

Compressibility ASTM F 36 A		12%
Recovery ASTM F 36 A		70%
Stress relaxation DIN 52913	50MPa, 16h/300 ⁰ C	39MPa
Klinger cold/hot compression	Thickness decrease 23 ⁰ C	9%
50MPa	decrease at 300 ⁰ C	7%
Chlorides (soluble)		150ppm
Thickness increase after fluid	Oil nr.3:5h/150 ⁰ C	3%
Immersion ASTM F 146	Fuel B:5h/23 ⁰ C	5%
Density		1.9g/cm ³