



KLINGERSil C-6307

Typical Specifications

Compressibility ASTM F 36 A		9-15%
Recovery ASTM F 36 A		45%
Klinger cold/hot compression (50MPa)	Thickness decrease 23 ⁰ C	10%
	decrease at 300 ⁰ C	28%
Gas leakage according to DIN 3535/6		0.5ml/min
Chlorides (soluble)		150ppm
Thickness increase after fluid	Oil No.3: 5h/150 ⁰ C	35%
Immersion ASTM F 146	Fuel B: 3h/23 ⁰ C	40%
Density		1.7g/cm ³